



Summary of Instrumented Impact Test Results:

Sample ID	Thickness (mm)	Maximum Load (KN)/ lb	Energy to Maximum Load (Joule / Ft-lbs)	Total Energy (Joule)	Total Energy (Ft. Lbs)	NTT Energy to Max Load (Joule/mm)	NTT Total Energy (Joule/mm)	Time to Maximum Load (msec)	Deflection to Maximum Load (mm)
ECOTEX Recycle Panels	4.8633	4.68/1052.1	21.74/16.09	41.0201	30.354	4.4672	8.4332	2.5585	8.4266